

- Condensate Polishing - Precoat

Microlite®

CG4H

Polystyrenic Powder, Cation / Anion
with Fiber, Hydrogen form,
Hydroxide form

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Polystyrene crosslinked with divinylbenzene	
Appearance	Powder	
Component Name	Cation	Anion
Polymer Structure	Styrene-Divinylbenzene	Styrene-Divinylbenzene
Functional Group	Sulfonic Acid	Quaternary Ammonium
Ionic Form	H ⁺ form	OH ⁻ form
Cation / Anion Ratio (dry weight basis)	1	1
Dry Weight Capacity (min.)	4.8 eq/kg	4 eq/kg
Site Composition on Hydrogen	99 %	
Site Composition on Hydroxide -max	95 %	
Site Composition on Chloride - max	0.1 %	
Site Composition on Sulfate - max	0.1 %	
Moisture Content (max.)	73 %	
Ratio F:R	1:1	
Standard Packaging Weight Dry Substance	5.5 Kg (12.1 lb)	
Color Code	Red	



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com