

# Purolite® NRW1000

Polystyrenic Gel, Strong Acid Cation Resin, Hydrogen form, Uniform Particle Size, Nuclear Grade

## PRINCIPAL APPLICATIONS

- Primary coolant polishing
- Radwaste decontamination
- Mixed Bed cation component
- Cation component before strong base anion
- Demineralization - Make Up Water

## ADVANTAGES

- Superior regeneration
- Highly converted to hydroxide form
- Minimal residual metals
- Low organic extractables and rinseables
- Superior separation

## SYSTEMS

- Make up water demineralizers
- Primary Coolant
- Radwaste

## TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H <sup>+</sup> form
Total Capacity	1.8 eq/L (39.3 Kgr/ft³) (H <sup>+</sup> form)
Moisture Retention	51 - 55 % (H <sup>+</sup> form)
Mean Diameter	570 ± 50 µm
Uniformity Coefficient (max.)	1.2
Conversion (min.)	99.9 % (H <sup>+</sup> form)
Impurities Iron (max.)	50 ppm
Impurities Sodium (max.)	40 ppm
Impurities Heavy Metals (max.)	40 ppm
Specific Gravity	1.20
Shipping Weight (approx.)	750 - 790 g/L (46.9 - 49.4 lb/ft³)
Temperature Limit	120 °C (248.0 °F)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com