

Purolite® NRW1160

Polystyrenic Gel, Strong Acid Cation
Resin, Hydrogen form, Uniform
Particle Size, Nuclear Grade

PRINCIPAL APPLICATIONS

- Secondary circuit polishing
- Layering on Polishing Mixed Beds

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

ADVANTAGES

- High operating capacity

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H ⁺ form
Total Capacity	2.5 eq/L (54.6 Kgr/ft ³) (H ⁺ form)
Moisture Retention	36 - 41 % (H ⁺ form)
Mean Diameter	625 ± 75 µm
Uniformity Coefficient (max.)	1.2
Conversion (min.)	99.9 % (H ⁺ form)
Impurities Iron (max.)	50 ppm
Impurities Sodium (max.)	40 ppm
Impurities Heavy Metals (max.)	40 ppm
Specific Gravity	1.23
Shipping Weight (approx.)	780 - 820 g/L (48.8 - 51.2 lb/ft ³)
Temperature Limit	120 °C (248.0 °F)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com