

PRODUCT DATA SHEET

Purolite® NRW3560

Polystyrenic Macroporous, Gel,
Mixed Bed Resin, Hydrogen form,
Hydroxide form, Nuclear Grade

PRINCIPAL APPLICATIONS

- Primary purification
- Demineralization - Steam Generator
Blowdown

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
Particle Size Range	425 - 1200 µm	
< 425 µm (max.)	2 %	
Uniformity Coefficient (max.)	1.7	
Impurities Iron (max.)	50 ppm	
Impurities Sodium (max.)	30 ppm	
Impurities Heavy Metals (max.)	40 ppm	
Anionic Form, CO ₃ ²⁻ (max.)	5 %	
Anionic Form, SO ₄ ²⁻ (max.)	0.1 %	
Anionic Form, Cl ⁻ (max.)	0.1 %	
Specific Gravity	1.08	
Shipping Weight (approx.)	720 - 750 g/L (45.0 - 46.9 lb/ft ³)	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Macroporous Strong Acid Cation	Gel Strong Base Anion
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H ⁺ form	OH ⁻ form
Cation / Anion Chemical Equivalent Ratio	1	1



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

Total Capacity (min.)	2.1 eq/L (H ⁺ form)	1.1 eq/L (OH ⁻ form)
Conversion (min.)	99.9 % (H ⁺ form)	95 % (OH ⁻ form)
Specific Gravity	1.21	1.08



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com