

- Condensate Polishing - Precoat

- 1 CF Box

Microlite® PrCH

Polystyrenic Powder, Cation,
Hydrogen form, Precoat

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Polystyrene crosslinked with divinylbenzene
Appearance	Powder
Functional Group	Sulfonic Acid
Ionic Form	H ⁺ form
Dry Weight Capacity (min.)	4.8 eq/kg
Moisture Content	45 - 62 %
< 10 µm (max.)	2 %
Whole Beads (min.)	
Site Composition on Hydrogen	99
Contaminants	Determined by the limit of ash analysis
Standard Packaging Weight Dry Substance	8.8 Kg (19.4 lb)
Typical Temperature Range	49 - 71 °C (120.2 - 159.8 °F)
Color Code	Red
Footnote	HIAC particle count



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com