

Supergel™ SGA550

Polystyrenic Gel, Type I Strong
Base Anion Resin, Chloride form,
Supergel™, Uniform Particle Size

PRINCIPAL APPLICATIONS

- Condensate Polishing

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

* Grade with antistat treatment is available as SGA550MB

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl ⁻ form
Total Capacity	1.4 eq/L (30.6 Kgr/ft ³) (Cl ⁻ form)
Moisture Retention	43 - 48 %
Mean Diameter	550 ± 50 µm
Uniformity Coefficient	1.1 - 1.2
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	24 %
Specific Gravity	1.09
Shipping Weight (approx.)	670 - 710 g/L (41.9 - 44.4 lb/ft ³)
Temperature Limit	100 °C (212.0 °F) (Cl ⁻ form)
Temperature Limit	60 °C (140.0 °F) (OH ⁻ form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com