

Supergel™ SGC650

Polystyrenic Gel, Strong Acid Cation
Resin, Sodium form, Supergel™

PRINCIPAL APPLICATIONS

- Condensate Polishing
- Condensate Softening

ADVANTAGES

- Excellent physical and chemical stability
- High breaking weight
- High linear velocity applications
- High operating capacity
- Lower pressure drop versus standard resin
- Superior osmotic shock resistance

SYSTEMS

- Condensate polishing mixed beds
- Condensate polishing lead cation
- High Temperature

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	Na ⁺ form
Total Capacity	2.2 eq/L (48.1 Kgr/ft³) (Na ⁺ form)
Moisture Retention	40 - 43 % (Na ⁺ form)
Mean Diameter	650 ± 50 µm
Uniformity Coefficient	1.1 - 1.2
Reversible Swelling, Na ⁺ → H ⁺ (max.)	8 %
Specific Gravity	1.3
Shipping Weight (approx.)	800 - 840 g/L (50.0 - 52.5 lb/ft³)
Temperature Limit	140 °C (284.0 °F)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com