



High flow SWRO T M 8 0 0 R

Туре	Diameter Inch	Membrane Area ft ² (m ²)	Salt Rejection %	Product Flow Rate gpd(m ³ / d)	Feed Spacer Thickness mil
TM820R-400	8"	400(37)	99.8	8,500(32.2)	34
TM820R-440	8"	440(41)	99.8	9,400(35.6)	28

1. Membrane Type		Cross Linked Fully Aromatic Polyamide Composite
2. Test Conditions		
	Feed Water Pressure	800 psi(5.52MPa)
	Feed Water Temperature	77°F(25°C)
	Feed Water Concentration	32,000 mg/l Nacl
	Recovery Rate	8%
	Feed Water pH	7
3. Minimum Salt Rejection		99.5%
4. Minimum Product Flow Rate		6,750gpd(25.6m ³ /d)(TM820R-400)
		7,500gpd(28.4m ³ /d)(TM820R-440)
5. Boron Rejection		95% at pH 8 (5mg/l Boron added to Feed water)
(typical value)		
		•

Dimensions





Operating Limits

	1200psi (8.3 MPa)
Maximum Feed Water Temperature	113°F (45°C)
Maximum Feed Water SDI15	5
Feed Water Chlorine Concentration	Not detectable
Feed Water pH Range, Continuous Operation	2-11
Feed Water pH Range, Chemical Cleaning	1-12
Maximum Pressure Drop per Element	15 psi (0.10 MPa)
Maximum Pressure Drop per Vessel	50 psi (0.34 MPa)

Operating Information

- 1.For the recommended design range, please consult the latest Toray technical bulletin, design guidelines, computer design program, and/ or call an application specialist. If the operating limits given in this Product Information Bulletin are not strictly followed, the Limited Warranty will be null and void.
- All elements are wet tested, treated with tested feed water solution, and then vacuum packed in oxygen barrier bags with deoxidant inside. To prevent biological growth during system shutdown, it is recommended to perform 30-60 minutes flushing of Toray elements with seawater once in every two days.
- 3. The presence of free chlorine and other oxidizing agents under certain conditions, such as heavy metals which acts as oxidation catalyst in the feed water will cause unexpected oxidation of the membrane. It is strongly recommended to remove these oxidizing agents contained in feed water before operating RO system.
- 4. Permeate from the first hour of operation shall be discarded.
- 5. The customer is fully responsible for the effects of chemicals that are incompatible with the elements. Their use will void the element Limited Warranty.

Notice

- 1. Toray accepts no responsibility for results obtained by the application of this information or the safety or suitability of Toray's products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product combination for their own purposes.
- 2. All data may change without prior notice, due to technical modifications or production changes.

Asia and Oceania: Toray Industries, Inc.	, , , , , , , , , , , , , , , , , , , ,	Europe, Middle East and Africa: Toray Membrane Europe AG	CHINA: Toray BlueStar Membrane Co., Ltd.
RO Membrane Products Department	Sales Office		
		Grabenackerstrasse 8	No.5 Anxiang Street, Area B,
1-1, Nihonbashi muromachi 2-chome	13435 Danielson St,	CH-4142 Münchenstein 1, Switzerland	Beijing Tianzhu Airport Economic Development Zone,
Chuo-ku, Tokyo 103-8666, Japan	Poway, CA 92064, USA	Tel: +41 61 415 87 10	Beijing ,101318 P.R.C.
Tel : +81 3 3245 4540	Tel: +1 858 218 2390	Fax: +41 61 415 87 20	Tel: +86 10 80490552
Fax: +81 3 3245 4913	Fax: +1 858 486 3063		Fax: +86 10 80485217
http://www.toraywater.com			